



## Kimya ABS-R

Kimya ABS-R 3D filament is a standard ABS based on 100% post-consumer recycled material from a recycling company based in France. Its use contributes to the development of a circular economy by reducing the emission of CO<sub>2</sub>, the consumption of water and electricity as well as the oil resources necessary for its production. Acrylonitrile butadiene styrene (ABS) is a thermoplastic polymer combining lightness, high impact resistance and good temperature resistance. ABS is suitable for functional prototyping, enclosure applications in industries such as appliances, telephony, automotive, hardware and toys.

- Better heat resistance than PLA (around 90°C) Good impact resistance
- Made from 100% post-consumer recycled ABS – reduced environmental impact
- Compliant with REACH regulation and RoHS directive

2-year KIMYA warranty.

Store away from light, humidity and heat to maintain the properties of the product

### FILAMENT PROPERTIES

PROPERTIES	TEST METHODS	VALUES
<b>Diameter</b>	INS-6712	1.75 ± 0.1 mm 2.85 ± 0.1 mm
<b>Density</b>	ISO 1183-1	1.049 g/cm <sup>3</sup>
<b>Moisture rate</b>	INS-6711	< 0.5 %
<b>Melt flow index (MFI)</b>	ISO 1133-1 (@210°C – 2,16 kg)	14.2 g/10min
<b>Glass transition temperature (T<sub>g</sub>)</b>	ISO 11357-1 DSC (10°C/min - 20-220°C)	110 °C

### PRINT PARAMETERS AND SPECIMENS DIMENSIONS

PRINTING DIRECTION	XY
<b>Printing Speed</b>	20-50 mm/s
<b>Infill</b>	100% - rectilinear
<b>Infill Angle</b>	45°/-45°
<b>Nozzle Temperature</b>	260°C
<b>Bed T°</b>	85-95°C

## PRINTED SPECIMENS PROPERTIES

	PROPERTIES	TEST METHODS	VALUES
<b>MECHANICAL PROPERTIES</b>	Tensile modulus	ISO 527-2/5A/50	1,722 MPa
	Tensile Strength	ISO 527-2/5A/50	32.2 MPa
	Tensile strain at strength	ISO 527-2/5A/50	2.1 %
	Tensile Stress at Break	ISO 527-2/5A/50	27.5 MPa
	Tensile strain at break (type A)	ISO 527-2/5A/50	9.4 %
	Flexural modulus	ISO 178	1,557 MPa
	Flexural stress at conventional deflection (3,5% strain)*	ISO 178	48.4 MPa
	Charpy impact resistance	ISO 179-1/1eA	8.5 kJ/m <sup>2</sup>
	Shore Hardness	ISO 868	72.2D
<b>Note 1</b>	*According to ISO 178, end of the test at 5% deformation even if there is no specimen break.		
<b>Note 2</b>	The data should be considered as indicative values - Properties can be influenced by production conditions.		

Created on 05/04/2023 - Revised on 05/04/2023.